

# POLYFRESKO® G SBS FR

## HIGHLY REFLECTIVE WHITE SBS (ELASTOMERIC) CAP SHEET

### PRODUCT DESCRIPTION

Polyfresko G SBS FR is a premium Styrene-Butadiene-Styrene (SBS) granulated cap sheet with fire retardant additives for use in low-slope roofing. Polyfresko G SBS FR is constructed with a superior non-woven polyester reinforcement that provides flexibility and dimensional stability as well as excellent tear and puncture resistance. Polyfresko G SBS FR has a film bottom surface for heat welding application.

Featuring patented CURE Technology®, Polyfresko G SBS FR has a highly reflective granule surface which meets, or exceeds most standards for cool roofing. CURE Technology features an innovative thin film technology attributing to exceptional granule retention, minimal staining, scuff resistance and UV stabilization for long-term durability and performance.

Polyfresko G SBS FR can be used as part of a Polyglass warranted multi-ply system, when combined with Elastoflex S6 or other approved Polyglass base sheets.

### TYPICAL APPLICATIONS

- Designed for heat-welded applications; burn-off film bottom surface.
- Applied directly over an acceptable substrate or as part of a multi-ply system.
- Ideal for new roofing, re-roofing, and for flashing details.

### FEATURES AND BENEFITS

- Suitable for most cool roof specifications; Solar Reflectance Index (SRI) Initial: 96, Aged: 82.
- Demonstrated to maintain exceptional reflectivity over time.
- Superior polyester mat for excellent tear and puncture resistance.
- Resistance to discoloration and scuffing.
- Exceptional granule retention; 0.11 g loss vs. ASTM max 2.0 g.
- FASTlap® granule free end lap provides faster, stronger seams.

### TECHNICAL DESCRIPTION\*

Physical Properties	CSA A123.23-15, Type B, Grade 1	Typical Performance
Strain Energy @-18°C – kN/m (lbf/in), Min	3.0 kN/m (17 lbf/in)	5.69 (32.49) - MD 7.62 (44.08) - XMD
Strain Energy @23°C – kN/m (lbf/in) before heat cond, Min	5.5 kN/m (31 lbf/in)	6.69 (38.20) - MD 6.47 (36.94) - XMD
Peak Load at -18°C (0°F) - kN/m (lbf/in), Min	Report Value**	21.89 (124.99) - MD 19.79 (113.00) - XMD
Elongation at Peak Load at -18°C (0°F) - (%), Min	Report Value**	52 - MD 77 - XMD
Peak Load at 23°C (73°F) - kN/m (lbf/in), Min	Report Value**	17.98 (102.67) - MD 13.48 (76.97) - XMD
Elongation at Peak Load at 23°C (73°F) - (%), Min	Report Value**	56 - MD 69 - XMD
Ultimate Elongation at 23°C (73°F) - (%) before heat cond, Min	Report Value**	60 - MD 77 - XMD
Low Temperature Flexibility* – °C (°F), Max	-18 (-4)	Pass
Dimensional Stability (%), Max	1.0	Pass
Compound Stability – °C (°F), Min	102 (205)	Pass
Resistance to Puncture – Pass/Fail	Pass	Pass
Granule Embedment – g (oz), Max	2.0 (0.07)	Pass

\*The properties in this table are “as manufactured” unless otherwise noted

\*\*Report Value: Shall be reported but has no minimum value.

### AVAILABLE COLORS

Highly Reflective White

Copyright ©2024 by Polyglass U.S.A., Inc. and all rights are reserved.

Edition Date: 09/24 • Doc# Polyfresko G SBS FR



### PRODUCT DATA\*\*\*

Net Coverage (Approx)..... 9.3 m<sup>2</sup> (100 ft<sup>2</sup>)  
 Weight (Approx) ..... 43 kg (97 lbs)  
 Thickness (Nominal) ..... 4.0 mm (160 mils)  
 Roll Size ..... 10 m × 1 m (32'10" × 39 3/8")  
 Rolls/Pallet..... 20

\*\*\*All values are nominal at time of manufacturing

### APPLICABLE STANDARDS

- ASTM D6164, Type I, Grade G
- UL Classified
- FM Approved
- ICC ESR-2018
- Texas Department of Insurance
- CRRC Listed
- Can be used to comply with 2016 Title 24 Part 6 Cool Roof requirements.
- Tested According to CSA A123.23-15, Type B, Grade 1



### PRODUCT CODES

- EPF40KCP



www.polyglass.ca


# POLYFRESKO® G SBS FR

## HIGHLY REFLECTIVE WHITE SBS (ELASTOMERIC) CAP SHEET

### APPLICATION INSTRUCTIONS

Polyfresko G SBS FR is intended to be used as the primary weathering surface in new or re-roof applications. Polyfresko G SBS FR is to be applied as the uppermost layer of a multi-ply roof system over a compatible Polyglass base or interply membrane. Polyfresko G SBS FR may be applied directly to certain non-combustible substrates.

- Apply over clean, dry, dust and debris-free substrates. When fully bonding, prime concrete decks and required substrates, prior to application with PG 100 Fast-Drying Asphalt Primer or alternative ASTM D41 primers as approved by Polyglass.
- When re-roofing, remove all prior roofing materials down to a clean debris-free substrate and properly close-off all abandoned roof penetrations.
- Concrete or steel decks shall be designed with proper expansion devices.
- Wood decks shall have all joints blocked and properly supported.
- Ensure the fire rating of the assembly over any combustible substrate.
- Ensure the installation of Polyfresko G SBS FR does not prevent the ventilation of existing construction.
- Do not apply over shingles or any granulated surface.
- While installing Polyfresko G SBS FR:
  1. Start at the low point of the roof.
  2. Unroll the material and allow to relax then re-roll the membrane once relaxed.
  3. Install with traditional torch roofing techniques ensuring proper heating of the roofing material. Fully torch the burnoff film creating a pool of asphalt. Pay close attention to the sidelap.
  4. Position successive rolls using the 5" FASTLap at the endlap and 3" granule free side lap. Asphalt bleed out shall be  $\frac{1}{4}$ " to  $\frac{3}{8}$ " on all seams.
  5. Use Polyglass' CURE Technology Detail and Repair Finish to treat seams on Polyfresko G SBS FR cap sheet. For more information, refer to CURE Technology Detail and Repair Finish Product Data Sheet.
- Details and flashing may be installed using hot asphalt, cold application or torch techniques. Check project details for proper installation requirements.
- For detailed drawings and recommended installation procedures of typical roof segments, such as drip edge and T-joint conditions, please refer to our website at, [www.polyglass.ca](http://www.polyglass.ca)

	<b>Rated Product ID #: 0616-0011a</b>		
		<b>Initial</b>	<b>Aged</b>
	<b>Solar Reflectance</b>	<b>0.77</b>	<b>0.68</b>
	<b>Thermal Emittance</b>	<b>0.90</b>	<b>0.88</b>
<small>The ratings above are subject to CRRC rating program conditions, requirements, and limitations. Visit <a href="http://coolroofs.org">coolroofs.org</a> for important information and disclaimers about CRRC rating conditions, requirements, and limitations.</small>			

**Solar Reflectance Index (SRI) – Initial: 96 • Aged: 82**

### MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

### CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.  
1111 West Newport Center Drive  
Deerfield Beach, FL 33442  
[www.polyglass.ca](http://www.polyglass.ca)

General Line: (888) 410-1375  
(954) 233-1330  
Customer Service: (800) 222-9782  
Technical Service: (866) 794-9659

**Questions?** [technical@polyglass.com](mailto:technical@polyglass.com)

**Product Disclaimer:** Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 5 years.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit [www.polyglass.ca](http://www.polyglass.ca).



[www.polyglass.ca](http://www.polyglass.ca)