

POLYSTICK® TU P

SELF-ADHERED REINFORCED GRANULE-SURFACED TILE UNDERLAYMENT

PRODUCT DESCRIPTION

Polystick TU P is self-adhered waterproofing underlayment specifically for use in adhesive foam* or mechanically fastened roof tile applications. Utilizing ADESO® dual-compound self-adhered technology, Polystick TU P features a polymer modified bitumen upper compound and a proprietary self-adhesive SBS (elastomeric) compound on the bottom. A split release film that protects the self adhesive compound allows for easy application.

The mineral granules used on the top surface of Polystick TU P provide maximum skid resistance as well as an extended exposure time of up to 36 months*. The combination of the unique surfacing, polyester-glass reinforcement and membrane thickness makes Polystick TU P an extremely robust, scuff and puncture resistant membrane with ultra long exposure times.

Polystick TU P features patented SEAllap® factory applied adhesive treatment at the membrane overlap which provides a quick watertight bond.

Although Polystick TU P is designed as an underlayment for clay and concrete tile coverings, this membrane can also be installed under slate tiles.

TYPICAL APPLICATIONS

- Adhesive set* and mechanically fastened roof tile applications.
- In difficult access areas where roof replacement is difficult.
- In situations when underlayment may be exposed for extended periods.

FEATURES AND BENEFITS

- Patented ADESO dual-compound self-adhered technology.
- Surface engineered for superior slip resistance.
- Extended exposure time of up to 36 months*.
- Tough 130 Mil thick polyester-glass mat reinforced; scuff and puncture resistant.
- Robust membrane holds-up to demands of heavy tile roofs.
- Asphaltic compound provides excellent sealability around nails.

TECHNICAL DESCRIPTION**

Physical Properties	ASTM Method	ASTM Value
Maximum Load, Longitudinal and Transverse, min, kN/m [lbf/in.]	D5147	4.4 [25]
Elongation at break, min of modified bitumen portion [%]	D5147	10
Tear Resistance, Longitudinal and Transverse, min, N [lbf]	D5147	89 [20]
Moisture Vapor Permeability, max, perms	E96	0.1
Adhesion to Plywood @ 40°F, min, lbf/ft width	D1970	2.0
Adhesion to Plywood @ 75°F, min, lbf/ft width	D1970	12.0
Sealability around nail	D1970	pass
Waterproof integrity after low temp flexibility	D1970	pass
Waterproof integrity of lap seam	D1970	pass
Slip Resistance	D1970	pass

*Refer to Florida Building Code and other local codes, listings, or requirements of the AHJ. Codes supersede Polyglass requirements and recommendations.

**The properties in this table are "as manufactured" unless otherwise noted.



PRODUCT DATA***

Net Coverage (Approx)100 ft² (9.3 m²)
 Gross Coverage 108 ft² (10 m²)
 Weight (Approx) 86 lbs (39 kg)
 Thickness (Nominal) 130 mils (3.3 mm)
 Roll Size32'10" × 39 3/8" (10 m × 1 m)
 Rolls/Pallet.....20

***All values are nominal at time of manufacturing

APPLICABLE STANDARDS

- ASTM D1970
- ICC ESR-1697
- Florida Building Code
- Miami-Dade County Approved
- Texas Department of Insurance



PRODUCT CODES

- PSTUP

POLYGLASS®



www.polyglass.us

POLYSTICK® TU P

SELF-ADHERED REINFORCED GRANULE-SURFACED TILE UNDERLAYMENT

APPLICATION INSTRUCTIONS

- Polystick TU P may be applied directly to the roof deck where allowable by Code, or to various approved substrates such as ASTM D226 type roofing felts and Polytherm insulation. For additional substrate requirements and information refer to Polyglass published "Suitable Substrates for Self-Adhered (SA) Membranes."
- Do not apply directly on to existing shingles or other roof coverings.
- Apply only when the substrate is dry and project related temperatures (air, roof deck, membrane) are 40°F and rising.
- Cut the Polystick TU P to a suitable, workable length prior to placement.
- Lay the material flat in place, starting at the lowest point. Overlap seams 3" at black side lap area and a minimum 6" at end laps.
- Peel half of the release film from the roll and apply firm, even pressure from the center to the outer edge. Remove the backing from the remaining half of the roll and apply pressure.
- Be sure to follow all local building code recommendations and requirements with regards to the width of ice dam materials.
- If full roof coverage application is desired, proper venting of the structure is recommended. Consult a design professional for proper venting requirements. Applications involving nonventilated attics or sheathing with radiant barriers, an anchor sheet is recommended to allow venting and prevent the creation of a double vapor barrier condition.
- In steep slope applications where back nailing may be recommended, be sure that all nails are covered by the overlapping next sheet.
- Polystick TU P must be covered within 36 months of installation or unless otherwise limited by the Authority Having Jurisdiction.
- Use PolyPlus® 50 or PG 500 to seal all end laps, hip and ridge details, and any conditions, patches or details over granules.
- Apply a bed of cement on any metals, vents, stacks, chimneys, and other roof accessories.
- Use on any repairs to the underlayment prior to application of the final roof covering.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330
Customer Service: (800) 222-9782
Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 1 year.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit www.polyglass.us.