

ELASTOFLEX® SA BASE SELF-ADHERED SBS ROOF MEMBRANE

PRODUCT DESCRIPTION

Elastoflex® SA Base membrane is a premium, self-adhered elastomeric base membrane, manufactured using patented ADESO® dual-compound self-adhesive technology, whereby a “true” Styrene-Butadiene-Styrene (SBS) modified asphalt compound is applied on the top layer and an aggressive self-adhesive compound is applied on the bottom layer. Elastoflex SA Base membrane has a high performance reinforced polyester mat to enhance puncture resistance and dimensional stability.

Elastoflex SA Base membrane is finished with polyolefin film having laylines on the top surface and a split release film on the bottom surface.

TYPICAL APPLICATIONS

- Designed for applications where using a propane torch is undesirable or prohibited
- Applications include new construction, re-roofing, and BUR repair installation
- Elastoflex SA Base was designed for use as an enhanced flashing reinforcement adding strength and dimensional stability to the critical flashing area, however can be used as a field membrane for for self-adhered, hot mopped, torch and cold adhesive systems

FEATURES AND BENEFITS

- Excellent long-term adhesion and application to multiple substrates and base plies
- Exceptional physical properties and long-term weathering performance
- Low temp flexibility, puncture and tear resistant

TECHNICAL DESCRIPTION

TEST METHOD	PROPERTY	ASTM VALUE
ASTM D5147	Maximum Load @ 23+/-2°C (73.4+/-3.6°F), MD and XMD, min, kN/m (lbf/in.)	4.4 (25)
ASTM D5147	Elongation at break 23+/-2°C (73.4+/-3.6°F), MD and XMD, min (%)	10%
ASTM D5147	Adhesion to Plywood, min at 40°F, lbf/ft width	2.0
ASTM D5147	Adhesion to Plywood, min at 75°F, lbf/ft width	12.0
ASTM D5147	Tear resistance N(lbf)	89 (20)
ASTM D5147	Sealability around nail	pass
ASTM D5147	Waterproof integrity after low temp flexibility	pass
ASTM D5147	Waterproof integrity of lap seam	pass
ASTM D5147	Slip Resistance	pass



PRODUCT DATA

Coverage (Approx).....	161 sq ft
Weight (Approx)	80 lbs
Thickness (Nominal).....	2.0 mm; 80 mils
Roll Size	1.5m x 1m (49.2' x 39.4")
Rolls/Pallet.....	20

APPLICABLE STANDARDS

- ASTM D1970



PRODUCT WARRANTY

Polyglass U.S.A., Inc. commercial roofing membranes can be backed with a manufacturer's warranty for up to 20 years when used as part of an approved, multi-ply roofing system. Please see your Polyglass U.S.A., Inc. Sales or Technical Representative for specifications and details.



www.polyglass.us

ELASTOFLEX® SA BASE

SELF-ADHERED SBS ROOF MEMBRANE

APPLICATION INSTRUCTIONS

Elastoflex SA Base is intended to be used as a high performance membrane flashing material, however can be used as a field membrane if desired for new or re-roof applications when applied to acceptable insulations and/or coverboards for commercial and residential structures. Elastoflex SA Base may also be applied directly to approved wood deck substrates of non-occupied spaces such as carports, sheds, canopies, etc.

- Apply only when the weather and forecast is dry and the ambient air temperature and substrate is 40°F (5°C) and rising.
- Apply over clean, dry, dust and debris free substrates. Prime concrete decks prior to application with PG 100 Asphalt Primer.
- When re-roofing, remove all prior roofing materials down to a clean debris free substrate and properly close off all abandoned roof penetrations.
- Concrete or Steel decks shall be designed with proper expansion devices.
- Wood decks shall be properly supported by the structural framing.
- Ensure the installation of Elastoflex SA Base does not prevent the ventilation of existing construction
- Do not apply directly to shingles or other granulated surface roof systems.
- While installing Elastoflex SA Base:
 1. Start at the low point of the roof.
 2. Unroll the material and allow to relax.
 3. Start by removing the first 18–24" of release film.
 4. Press the membrane into place with firm and even pressure. Roll the edges with a silicone hand roller to ensure complete adhesion.
 5. Gradually remove the remaining release film applying pressure from the center to the edges as you go.
 6. Position successive rolls providing a minimum 6" end lap and 4" side lap. Laps can be sealed for additional water tightness with a hot air welder.
 7. Roll with an 80# split-face linoleum roller. Take care on sloped roofs by securing the roller and applicator with the appropriate safety equipment.
- Details and flashing may be installed using Elastoflex SA Base with a hot air welder or with PG 500 Roof Cement. Check project details for proper installation requirements.

POLYGLASS U.S.A., INC. MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Phoenix, AZ
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330
Customer Service: (800) 222-9782
Technical Service: (866) 802-8017

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 2 years.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control.

For most current product data and warranty information, visit www.polyglass.us

Copyright ©2016 by Polyglass U.S.A., Inc and all rights are reserved
Edition Date: 06/16 • Doc# Elastoflex SA Base



www.polyglass.us