

# ELASTOFLEX V G

## SBS (ELASTOMERIC) GRANULATED CAP SHEET

### PRODUCT DESCRIPTION

Elastoflex V G is an SBS (elastomeric) modified bitumen low-slope roofing membrane cap sheet. This durable membrane is reinforced with a high quality fiberglass mat to ensure strength and excellent dimensional stability to the product. The proprietary SBS compound offers superior waterproofing and weathering physical properties. Elastoflex V G is configured with a sand backing for hot mop or cold process applications.

Elastoflex V G membrane can be used as part of a Polyglass warranted multi-ply system, when combined with Elastoflex V base or interply sheets or other approved Polyglass base sheets.

### TYPICAL APPLICATIONS

- Use as a cap ply for multi-ply systems.
- New roofing, re-roofing and re-cover roofing and flashing details.
- Hot asphalt and cold process installation methods.

### FEATURES AND BENEFITS

- High quality SBS compound for exceptional long-term weathering performance.
- Fiberglass mat enhances strength and dimensional stability.

### TECHNICAL DESCRIPTION\*

| Physical Properties                      | ASTM Method | ASTM Value               | Typical Performance                                          |
|------------------------------------------|-------------|--------------------------|--------------------------------------------------------------|
| Peak Load at 0 °F (-18 °C)               | D 5147      | 70 lbf/in<br>(12.3 kN/m) | 145 lbf/in (25.4 kN/m) - MD<br>97 lbf/in (17.0 kN/m) - XMD   |
| Elongation at Peak Load at 0 °F (-18 °C) | D 5147      | 1%                       | 6.0% - MD 5.0% - XMD                                         |
| Peak Load at 73 °F (23 °C)               | D 5147      | 30 lbf/in<br>(5.3 kN/m)  | 82.0 lbf/in (14.4 kN/m) - MD<br>50.0 lbf/in (8.8 kN/m) - XMD |
| Elongation at Peak Load at 73 °F (23 °C) | D 5147      | 2%                       | 5.0% - MD<br>4.4% - XMD                                      |
| Ultimate Elongation at 73 °F (23 °C)     | D 5147      | 3%                       | 40% - MD<br>57% - XMD                                        |
| Tear Strength at 73 °F (23 °C)           | D 5147      | 35 lbf (156 N)           | 112 lbf (498 N) - MD<br>101 lbf (449 N) - XMD                |
| Low Temperature Flexibility (maximum)    | D 5147      | 0 °F (-18 °C)            | PASS                                                         |
| Dimensional Stability, max %             | D 5147      | 0.50%                    | 0.1% - MD<br>0.1% - XMD                                      |
| Compound Stability (pass/fail)           | D 5147      | 215 °F (102 °C)          | PASS                                                         |
| Granule Embedment (maximum loss)         | D5147       | 2 g                      | 1.9 g                                                        |

\*The properties in this table are "as manufactured" unless otherwise noted

### AVAILABLE COLORS

Black (BL)                      Buff (BU)                      White (WH)



### PRODUCT DATA\*\*

Net Coverage (Approx) .... 100 ft<sup>2</sup> (9.3 m<sup>2</sup>)  
 Weight (Approx) ..... 90 lb (41 kg)  
 Thickness (Nominal) ..... 140 mils (3.5 mm)  
 Roll Size ..... 32'10" x 39 3/8" (10 m x 1 m)  
 Rolls/Pallet ..... 20

\*\*All values are nominal at time of manufacturing

### APPLICABLE STANDARDS

- ASTM D6163, Type I, Grade G;
- ASTM D3909
- UL Classified
- FM Approved
- ICC ESR-2018
- Florida Building Code
- Miami-Dade County Approved
- Texas Department of Insurance



### PRODUCT CODES

- EF35##S (Granule/Sand)
- ##denotes color code - see Available Colors



[www.polyglass.us](http://www.polyglass.us)

# ELASTOFLEX V G

## SBS (ELASTOMERIC) GRANULATED CAP SHEET

### APPLICATION INSTRUCTIONS

Elastoflex V G is intended to be used as the primary weathering surface in new or re-roof applications. Elastoflex V G is to be applied as the uppermost layer of a multi-ply roof system applied over a compatible Polyglass base or interply membrane. Elastoflex V G may be applied directly to certain non-combustible substrates.

- Apply over clean, dry, dust and debris-free substrates. Prime concrete decks and required substrates prior to application with PG 100 Fast-Drying Asphalt Primer. Consult Polyglass Technical Service if alternate primer is allowed.
- When re-roofing, remove all prior roofing materials down to a clean debris-free substrate and properly close-off all abandoned roof penetrations.
- Concrete or steel decks shall be designed with proper expansion devices.
- Wood decks shall have all joints blocked and properly supported.
- Ensure the fire rating of the assembly over any combustible substrate.
- Ensure the installation of Elastoflex V G does not prevent the ventilation of existing construction.
- Do not apply over shingles or any granulated surface.
- While installing Elastoflex V G:
  1. Start at the low point of the roof.
  2. Unroll the material and allow to relax then re-roll the membrane once relaxed.
  3. Install in a solid mopping of Type III or Type IV asphalt or PG 350 Mod Bit Adhesive. Pay close attention to the sidelap.
  4. Position successive rolls providing a minimum 6" end lap and 3" side lap.
  5. Matching loose granules may be sprinkled onto the bleed out.
- Details and flashing may be installed using hot asphalt or cold application techniques. Check project details for proper installation requirements.

### MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

### CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.  
1111 West Newport Center Drive  
Deerfield Beach, FL 33442  
[www.polyglass.us](http://www.polyglass.us)  
General Line: (888) 410-1375  
(954) 233-1330  
Customer Service: (800) 222-9782  
Technical Service: (866) 802-8017

**Questions?** [technical@polyglass.com](mailto:technical@polyglass.com)

**Product Disclaimer:** Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 5 years.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit [www.polyglass.us](http://www.polyglass.us)

