

POLYFRESKO® G SBS HP FR

HIGHLY REFLECTIVE WHITE SBS (ELASTOMERIC) CAP SHEET

PRODUCT DESCRIPTION

Polyfresko G SBS HP FR is a premium Styrene-Butadiene-Styrene (SBS) granulated cap sheet with fire retardant additives for use in low-slope roofing. Polyfresko G SBS HP FR is constructed with a high performance non-woven polyester reinforcement that provides flexibility and dimensional stability as well as excellent tear and puncture resistance. Polyfresko G SBS HP FR has a film bottom surface for heat welding application.

Featuring patented CURE Technology®, Polyfresko G SBS HP FR has a highly reflective granule surface which meets, or exceeds most standards for cool roofing. CURE Technology features an innovative thin film technology attributing to exceptional granule retention, minimal staining, scuff resistance and UV stabilization for long-term durability and performance.

Polyfresko G SBS HP FR can be used as part of a Polyglass warranted multi-ply system, when combined with Elastoflex S6 or other approved Polyglass base sheets.



TYPICAL APPLICATIONS

- Designed for heat-welded applications; burn-off film bottom surface.
- Applied directly over an acceptable substrate or as part of a multi-ply system.
- Ideal for new roofing, re-roofing, and for flashing details.

FEATURES AND BENEFITS

- Suitable for most cool roof specifications; Solar Reflectance Index (SRI) Initial: 96, Aged: 82.
- Demonstrated to maintain exceptional reflectivity over time.
- Superior polyester mat for excellent tear and puncture resistance.
- Resistance to discoloration and scuffing.
- Exceptional granule retention; 0.11 g loss vs. ASTM max 2.0 g.
- FASTlap® granule free end lap provides faster, stronger seams.

TECHNICAL DESCRIPTION*

Physical Properties	CSA A123.23-15, Type B, Grade 1	Typical Performance
Strain Energy @-18°C – kN/m (lbf/in), Min	3.0 kN/m (17 lbf/in)	9.58 (54.70) - MD 4.96 (28.32) - XMD
Strain Energy @23°C – kN/m (lbf/in) before heat cond, Min	5.5 kN/m (31 lbf/in)	10.00 (57.11) - MD 5.59 (31.94) - XMD
Peak Load at -18°C (0°F) - kN/m (lbf/in), Min	Report Value**	9.54 (111.58) - MD 12.33 (70.41) - XMD
Elongation at Peak Load at -18°C (0°F) - (%), Min	Report Value**	51 - MD 42 - XMD
Peak Load at 23°C (73°F) - kN/m (lbf/in), Min	Report Value**	17.43 (99.53) - MD 9.52 (54.36) - XMD
Elongation at Peak Load at 23°C (73°F) - (%), Min	Report Value**	72 - MD 67 - XMD
Ultimate Elongation at 23°C (73°F) - (%) before heat cond, Min	Report Value**	127 - MD 186 - XMD
Low Temperature Flexibility* – °C (°F), Max	-18 (0)	Pass
Dimensional Stability (%), Max	1.0	Pass
Compound Stability – °C (°F), Min	102 (205)	Pass
Resistance to Puncture – Pass/Fail	Pass	Pass
Granule Embedment – g (oz), Max	2.0 (0.07)	Pass

*The properties in this table are “as manufactured” unless otherwise noted

**Report Value: Shall be reported but has no minimum value.

AVAILABLE COLORS

Highly Reflective White

Copyright ©2024 by Polyglass U.S.A., Inc. and all rights are reserved.

Edition Date: 09/24 • Doc# Polyfresko G SBS HP FR



PRODUCT DATA***

Net Coverage (Approx)..... 9.3 m² (100 ft²)
 Weight (Approx) 50 kg (110 lbs)
 Thickness (Nominal) 4.2 mm (165 mils)
 Roll Size 10 m × 1 m (32'10" × 39 3/8")
 Rolls/Pallet..... 20

***All values are nominal at time of manufacturing

APPLICABLE STANDARDS

- ASTM D6164
- UL Classified
- CRRC Listed
- Meets the requirements of California Energy Commission (CEC) Title 24 Section 110.8 (i)4.
- CSA A123.23-15, Type B, Grade 1



PRODUCT CODES

- EPHF40KCP



www.polyglass.ca


POLYFRESKO® G SBS HP FR

HIGHLY REFLECTIVE WHITE SBS (ELASTOMERIC) CAP SHEET

APPLICATION INSTRUCTIONS

Polyfresko G SBS HP FR is intended to be used as the primary weathering surface in new or re-roof applications. Polyfresko G SBS HP FR is to be applied as the uppermost layer of a multi-ply roof system over a compatible Polyglass base or interply membrane. Polyfresko G SBS HP FR may be applied directly to certain non-combustible substrates.

- Apply over clean, dry, dust and debris-free substrates. When fully bonding, prime concrete decks and required substrates, prior to application with PG 100 Fast-Drying Asphalt Primer or alternative ASTM D41 primers as approved by Polyglass.
- When re-roofing, remove all prior roofing materials down to a clean debris-free substrate and properly close-off all abandoned roof penetrations.
- Concrete or steel decks shall be designed with proper expansion devices.
- Wood decks shall have all joints blocked and properly supported.
- Ensure the fire rating of the assembly over any combustible substrate.
- Ensure the installation of Polyfresko G SBS HP FR does not prevent the ventilation of existing construction.
- Do not apply over shingles or any granulated surface.
- While installing Polyfresko G SBS HP FR:
 1. Start at the low point of the roof.
 2. Unroll the material and allow to relax then re-roll the membrane once relaxed.
 3. Install with traditional torch roofing techniques ensuring proper heating of the roofing material. Fully torch the burnoff film creating a pool of asphalt. Pay close attention to the sidelap.
 4. Position successive rolls using the 5" FASTLap at the endlap and 3" granule free side lap. Asphalt bleed out shall be $\frac{1}{4}$ " to $\frac{3}{8}$ " on all seams.
 5. Use Polyglass' CURE Technology Detail and Repair Finish to treat seams on Polyfresko G SBS HP FR cap sheet. For more information, refer to CURE Technology Detail and Repair Finish Product Data Sheet.
- Details and flashing may be installed using hot asphalt, cold application or torch techniques. Check project details for proper installation requirements.
- For detailed drawings and recommended installation procedures of typical roof segments, such as drip edge and T-joint conditions, please refer to our website at, www.polyglass.ca

	Rated Product ID #: 0616-0011a		
		Initial	Aged
	Solar Reflectance	0.77	0.68
	Thermal Emittance	0.90	0.88
<small>The ratings above are subject to CRRC rating program conditions, requirements, and limitations. Visit coolroofs.org for important information and disclaimers about CRRC rating conditions, requirements, and limitations.</small>			

Solar Reflectance Index (SRI) – Initial: 96 • Aged: 82

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.ca

General Line: (888) 410-1375
(954) 233-1330
Customer Service: (800) 222-9782
Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 5 years.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit www.polyglass.ca.



www.polyglass.ca